

## ROYALTUF<sup>®</sup> 527

### Polymer Modifier

ROYALTUF<sup>®</sup> 527 is a maleic anhydride modified ethylene-propylene-non-conjugated diene (EPDM) terpolymer.

**CAS Number 25038-36-2**

#### Typical Physical Properties of ROYALTUF<sup>®</sup> 527

Property	Typical Value	Test Based On
Appearance	Off-white Rubbery Pellet	Visual
EPDM Backbone	Amorphous Elastomer	DSC
Mooney Viscosity (1+4) @ 125°C	30	ASTM D-1646
Maleic Anhydride Content	High*	ASTM D-6047
Density @ 23°C	0.87 g/cm <sup>3</sup>	ASTM D-792
Bulk Density	0.6 g/cm <sup>3</sup> (maximum)	ASTM D-1895B
Glass Transition Temperature (Tg)	-47°C	DSC

\* High = Maleic Anhydride Content typically in the range of 0.8 to 1.2%.

#### Applications

- Rubbery modifier for polyamides polymers providing improved impact resistance at room temperature
- Amorphous backbone imparting highest impact properties in polyamides at temperatures down to -40°C
- Impact modifier giving “Super-Tough” polyamide properties when used at 20% loading
- Free flowing pellets are dusted facilitating storage and handling

#### Food Contact

Check with the Product Safety and Regulatory Affairs Department of Addivant<sup>™</sup> for current status.

#### Regulatory Status

The components of ROYALTUF<sup>®</sup> 527 are listed on USA TSCA inventory. For information on other inventory listings, see Section 15 (Regulatory Information) of the MSDS for ROYALTUF<sup>®</sup> 527.

#### Storage & Handling Precautions

ROYALTUF<sup>®</sup> 527 is coated with micro-pulverized polyethylene dusting agent. Dust generated during handling and processing can be irritating. Provide proper ventilation and dust collection at machinery. Fine dust dispersed in air may ignite. Keep away from heat and sources of ignition. Keep containers tightly closed when stored. Store in a dry, well-ventilated space.

#### For additional handling and toxicological information consult the Addivant<sup>™</sup> Material Safety Data Sheet

The information contained herein relates to a specific Addivant<sup>™</sup> product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. Nothing in this Technical Data Sheet shall be construed to modify any of Addivant<sup>™</sup> standard terms and conditions of sale under which the product is sold by Addivant<sup>™</sup>. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCT'S CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND ANY AND ALL SUCH REPRESENTATIONS AND WARRANTIES ARE HEREBY EXPRESSLY DISCLAIMED. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

Addivant<sup>™</sup> and the Addivant<sup>™</sup> logo are trademarks of Addivant<sup>™</sup> Corporation or one of its subsidiaries.

Copyright © 2013 Addivant<sup>™</sup> Corporation. All rights reserved.