

**IMUTHANE**
CASTABLE POLYURETHANE
ELASTOMERS
27-58D**IMUTHANE**
27-58D

IMUTHANE 27-58D is a MDI / POLYETHER based prepolymer which yields a 58 Shore-D elastomer when cured with 1, 4 butanediol (BDO).

Typical Prepolymer Properties

% NCO	12.3 – 12.7
Brookfield Viscosity @ 100° C	1.0 – 4.0
Specific Gravity @ 77° F (25° C)	1.11
@ 212° F (100° C)	1.05

Typical Process Conditions

IMUTHANE 27-58D °F (°C)	180 (82)
BDO, °F (°C)	77 (25)
Mold, °F (°C)	240 (115)
% Theory	95
Pot Life, min	3
Cure Time, min @ °F (°C)	60 @ 240 (115)
Post Cure, hrs @ °F (°C)	16 @ 240 (115)

Typical Physical Properties

Shore Hardness	58D
100% Modulus, psi (MPa)	2500 (17.2)
300% Modulus, psi (MPa)	3805 (26.5)
Tensile, psi (MPa)	5400 (37.3)
Elongation, %	450
Tear Strength, Die C, pli (kN/m)	750 (131.3)
Tear Strength, (D470), pli (kN/m)	50 (8.8)
Bashore Rebound, %	45
Compression Set, Method B, 22 hrs @ 158°F (70°C), %	30
Specific Gravity	1.11

The data contained herein are believed to be reliable. However, there is no guarantee that the same results will be obtained under different conditions. Fit for use testing should be conducted by each user.